

Accura® CastPro™ Free (SL 7800)

Stable material for casting patterns free of heavy metals using QuickCast™ technology



Technical Data

Post-Cured Material

Measurement	Condition	Metric	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	45-48	6530-6960
Tensile Modulus (MPa/KSI)	ASTM D 638	1940-2350	281-341
Elongation at Break	ASTM D 638	9-19 %	9-19 %
Flexural Strength (MPa/PSI)	ASTM D 790	81-83	11750-12035
Flexural Modulus (MPa/KSI)	ASTM D 790	2200-2480	319-360
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	35-50	0.66-0.94
Heat Deflection Temperature	ASTM D 648 @ 66 PSI	62 °C	144 °F
Coefficient of Thermal Expansion (CTE)	ASTM E 831-93 25-50 °C	100 µ mm/m °C	55 µin/in °F
Glass Transition (Tg)	DMA, E"	57 °C	134 °F
Shore D		87	87

Liquid Material


Measurement	Condition	Value
Viscosity	@ 30 °C (86 °F)	205 cps
Penetration Depth (Dp)		5.74 mils
Critical Exposure (Ec)		9.98 mJ/cm²
Color		Clear Amber
Solid Density	@ 25 °C (77 °F)	1.15 g/cm³
Liquid Density	@ 25 °C (82 °F)	1.12 g/cm³

Features

- Produce accurate QuickCast™ patterns
- Excellent humidity/moisture resistance
- Free of antimony for cleaner burnout



20 Executive Drive Hudson, NH 03051
Austin Wong | 603.546.6812 | austin.wong@vaupell.com



3DSYSTEMS®

3D Systems Corporation Tel: +1 803.326.3900
333 Three D Systems Circle NYSE: DDD
Rock Hill, SC 29730, USA www.3dsystems.com

MANUFACTURING THE FUTURE

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2015 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. CastPro and QuickCast are trademarks, the 3D logo and Accura are registered trademarks of 3D Systems, Inc.